

TECHNICAL DATA SHEET

DIMENSIONS

FORMAT

Width	1261 mm
Length	192 mm
Number of panels per pack	9
m ² per pack	2.179
Bevels	-
Thickness	8.0 mm
Tongue and groove	Uniclic water resistant surface

FACTORY WARRANTY

	METHOD	PARAMETERS	VALUES
Usage class	EN 13329		Class
CE	EN 14041		21-22-23/31-32
Warranty	Residential use	See warranty conditions	
	Commercial use	See warranty conditions	
	Water resistancy	See warranty conditions	

GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Wear resistance	EN 13329		≥ 4000 cycles	≥ 4000 cycles
Wear class	EN 13329		AC4	AC4
Impact resistance	EN 13329		IC2	IC2
Scratch resistance	EN 438-2, 25		Charge ≥ 3N	Charge ≥ 3N
Effect of a castor chair	ISO 4918 (with underlay)	T _{type W} (EN 12529)	25000 cycles	No change
Thickness swelling	ISO 24336	After 24h immersion at 20°C	≤ 18%	≤ 18%
		F10,2 long side	≥ 1 kN/m	≥ 1 kN/m
		F _{max} long side	≥ 2 kN/m	≥ 2 kN/m
Locking strength	ISO 24334	F _{s0,2} short side	≥ 2 kN/m	≥ 2 kN/m
		F _{max} short side		≥ 2 kN/m
Effect of a furniture leg	EN 424		No damage shall be visible, when tested with foot type 0	No visible damage
Resistance to staining	EN 438	Group 1,2	Class 5	Class 5
		Group 3	Class 4	Class 4
Light fastness	EN ISO 105 B02	Blue reference	Class ≥ 6	Class 6

ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Formaldehyde emission	EN 717-1	ppm	E1 < 0,1	< 0,01
Reaction to fire	EN 13501-1	Class		Cfl-s1
Thermal resistance	EN 12996:2001	m ² K/W		0,0717 m ² K/W
Slip resistance	EN 13893	μ	μ ≥ 0,30	DS: μ ≥ 0,30



EN14041:2004/AC:2006
Laminate floor coverings EN13329:2004-11